

Hydrotech® Hydrocap 160FR

formerly known as Hydrocap 160FR



BUILDING TRUST



GENERAL DESCRIPTION

Hydrocap 160FR is a specially formulated, heavy duty, rubberized asphalt protection/cap sheet that is reinforced with a tough, dimensionally stable non-woven polyester mat that is saturated and coated on both sides with elastomeric styrene-butadiene-styrene (SBS) polymer modified bitumen, with a fire rated, non-combustible, ceramic granular surface. Meets or exceeds requirements of ASTM D6163, Type I, Grade G.

BASIC USE

Hydrocap 160FR is specifically designed to be embedded into Hydrotech's Monolithic Membrane 6125® roofing and waterproofing membrane assemblies to act as both protection for the membrane and the finished surface of the roof.

Additional protection is normally required in traffic areas and where physical abuse is anticipated.



PRODUCT INFORMATION

- Roll size - 39.4" x 32.8'
- Roll weight (lbs) - 118
- Roll thickness (mils) - 160
- Roll coverage w/3" lap (sq/ft) - 100

TECHNICAL DATA

PROPERTY	TEST METHOD	RESULTS
SOLAR REFLECTANCE INDEX (SRI)	ASTM E1980	25
PEAK LOAD (lbf/in. @73.4°F)	ASTM D5147	85MD; 65XMD
PEAK LOAD (lbf/in. @0°F)	ASTM D5147	115MD; 90XMD
LOW TEMPERATURE FLEXIBILITY (32°F)	ASTM D5147	-15(MD), -15(XMD)
ELONGATION AT PEAK LOAD (% @ 0°F)	ASTM D5147	35MD; 40XMD
ELONGATION AT PEAK LOAD (% @73.4°F)	ASTM D5147	55MD; 60XMD
ULTIMATE ELONGATION (% @73.4°F)	ASTM D5147	65MD; 80XMD
TEAR STRENGTH (@73.4°F; lbf)	ASTM D5147	125MD; 85XMD
DIMENSIONAL STABILITY (%)	ASTM D5147	<0.5MD; <0.5XMD
COMPOUND STABILITY (°F)	ASTM D5147	240(MD), 240(XMD)
GRANULE EMBEDMENT	ASTM D5147	1.5 avg

Data is represented by average values, unless noted otherwise.

LEED INFORMATION

	Credit 4	Credit 5
Recycled Content (% by weight)	0%	
Manufacture Location		Medina, OH & Gulfport, MS
Extraction/Harvesting Location		Medina, OH & Gulfport, MS - Asphalt - 30% - 70%

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at usa.sika.com or by calling SIKA's Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.**

Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/group/SikaCorp/termsandconditions.html> or by calling 1-800-933-7452.