# Hydrotech<sup>®</sup> Root Stop - Standard

formerly known as Root Stop - Standard

## **GENERAL DESCRIPTION**

Root Stop is a 10 mil, smooth, high quality polyethylene geo-membrane sheeting produced from specially formulated, virgin polyethylene resin.

## **BASIC USE**

Root Stop is designed to be used as a root barrier for Hydrotech<sup>®</sup> Monolithic Membrane 6125<sup>®</sup> as part of Hydrotech's Garden Roof<sup>®</sup> Assembly. Root Stop is especially designed for use in extensive assemblies with herbaceous plants only (no woody plant varieties), lawn applications with no woody plants, and planters with herbaceous plants only. Root Stop is loose laid over Hydroflex<sup>®</sup> 30, and lapped 5 feet or lapped 2.5 feet with the lap edges taped with Root Stop Tape.

#### SIZES

Root Stop is available in rolls 15 feet (4.57 m) wide by 100 feet (30.48 m) long for a full roll (950 sq.ft effective coverage with 5 foot laps and 1,218 sq.ft effective coverage with 2.5 foot laps).

## **TECHNICAL DATA**

| PROPERTY   | TEST METHOD                    | RESULTS     |
|--|--------------------------------|-------------|
| THICKNESS mils (mm)  | ASTM D5199                     | 10 (0.25)   |
| WEIGHT lb/ft <sup>2</sup> (kg/m <sup>2</sup> )                 | ASTM D1505                     | 0.05 (0.24) |
| TENSILE STRENGTH lb/in, avg, (N)<br>Machine & Cross Directions | ASTM E154, Section 9<br>(D882) | 52 (230)    |
| PUNCTURE RESISTANCE Ib (kg)                                    | ASTM D1709, Method B           | 4.85 (2.20) |
| PERMEANCE Perms (Grains/(ft² • hr • in • Hg)                   | ASTM E154 Section 7 E96        | 0.0146      |
| AFTER CONDITIONING   | ASTM E154 Section 8 E96        | 0.0153      |
| WVTR grain/hr•ft <sup>2</sup>                                  | ASTM E96 Procedure B           | 0.0084      |

#### **LEED® INFORMATION**

|                                | Credit 4 | Credit 5        |
|--------------------------------|----------|-----------------|
| Recycled Content (% by weight) | 0        |                 |
| Manufacture Location           |          | Sioux Falls, SD |
| Extraction/Harvesting Location |          | Sioux Falls, SD |

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at usa.sika.com or by calling SIKA's Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.

Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at https://usa.sika.com/en/group/SikaCorp/termsandconditions.html or by calling 1-800-933-7452.

Sika Corporation • Roofing & Waterproofing 100 Dan Road, Canton, MA 02021 USA • (888) 509-3350 • 4/25

usa.sika.com | hydrotechusa.com



