

# Surface Conditioner



A SIKA COMPANY

## GENERAL DESCRIPTION

An asphaltic concrete surface conditioner.

## BASIC USE

To enhance the bond of American Hydrotech’s Monolithic Membrane 6125® roofing and waterproofing membranes to concrete substrates.

## TECHNICAL SPECIFICATIONS

Must conform to CGSB 37-GP-9Ma.

## SIZES

Surface Conditioner is available 5 gallon pails (40 lbs, 18.1 kg) or 55 gallon drums (440 lbs, 199.6 kg).



## APPLICATION

- Thoroughly clean area to be waterproofed. The area must be thoroughly swept, then blown clean using an air compressor.
- The Surface Conditioner is then spray-applied at a rate of 300-600 square feet per gallon. The result should be a “tanning” of the concrete surface. Over-application may cause adhesion problems between the concrete and MM6125.
- The Surface Conditioner must be allowed sufficient time to thoroughly dry. **NOTE:** The cooler the ambient temperature and/or higher the humidity, the more drying time required.
- **DO NOT** apply Surface Conditioner to wood, plywood, metal or gypsum board substrates - concrete only.
- The Surface Conditioner can be cut-back with unleaded gas if necessary, to facilitate spraying.

## CAUTIONS

### FLAMMABLE MATERIAL!

Do not use near open fire or flame and extinguish all smoking materials.

## LEED INFORMATION

	Credit 4	Credit 5
Recycled Content (% by weight)	0	
Manufacture Location		Montreal, QC
Extraction/Harvesting Location		Montreal, QC
VOC Content (g/L)		540

This information is intended only for general conceptual purposes. It is based on data and knowledge considered to be true and correct. It is offered for the user’s consideration, investigation and verification and is not intended to substitute for the advice provided by appropriate professionals. Hydrotech assumes no liability for the use of this information. The determination of the suitability and applicability of this information is the sole responsibility of the user.