

HydroSeal Thixo Liquid



GENERAL DESCRIPTION

HydroSeal Thixo Liquid is a thixotropic additive for HydroSeal PMMA based resins as recommended.

BASIC USE

HydroSeal Thixo Liquid is mixed with HydroSeal PMMA resins as required for application on slopes greater than 1-1/2:12.

APPLICATION

Thoroughly mix the entire drum of HydroSeal resin being altered for 2 - 3 minutes before each use, and prior to pouring off resin into a second container if batch mixing. Add HydroSeal Thixo Liquid to the resin component, stir for 2 minutes using a slow-speed mechanical agitator. Allow resin to stand approximately 20 minutes with Thixo Liquid before use. Refer to specific HydroSeal resin product data sheet for recommendations regarding catalyzing and application of resin.

Storage and working times are not affected by addition of this additive. Refer to the HydroSeal resin product data sheet for specific working times.

PACKAGING/SIZES/COVERAGE

HydroSeal Thixo Liquid is supplied in 1 kg bottles.

HydroSeal Thixo Liquid is added to recommended HydroSeal resins by weight as follows:

HydroSeal Finish White:	1%
HydroSeal Resin:	2%

Always store in a cool and dry location. Do not store in direct sunlight or in temperatures below 32°F(0°C) or above 77°F(25°C). Approximate shelf life is 12-months when left sealed and with proper storage.

PRECAUTIONS

Refer to product Material Safety Data Sheet (MSDS) prior to use or handling.

Always store in cool and dry location. Do not store in direct sunlight or in temperatures below 32°F (0°C) or above 77°F (25°C). Approximate shelf life is 6 months when left sealed, unmixed and with proper storage.

This information is intended only for general conceptual purposes. It is based on data and knowledge considered to be true and correct. It is offered for the user's consideration, investigation and verification and is not intended to substitute for the advice provided by appropriate professionals. Hydrotech assumes no liability for the use of this information. The determination of the suitability and applicability of this information is the sole responsibility of the user.